

m/s Beaulieu of Australia Attn: MS Sue Schultz
64 Lahrs Rd, Ormeau Q/Ld 4208

TEST REPORT No. 125509

LABORATORY REF: P125509

CUSTOMER REFERENCE
CRITICS CHOICE

Sample description as provided by customer

Order No. 285395

Mass/unit area 26 oz/yd²

Pile Fibre Content 100% RESISTAIN SOLUTION DYED NYLON

Construction Details Tufted Secondary Backing Synthetic

Colour Natural Canvas 46

Style Cut Pile

Pile Height 6 mm

TEST METHOD AS/ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by specification C1.10a of the Building Code of Australia.

Tested in accordance with the Carpet Institute Code of Practice for AS/ISO 9239 Testing Version 10 / 0805.

The test values relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use. Clause 9 of AS/ISO 9239 Part 1.

Conditioning as specified in BS EN 13238.2001

Sample submitted Date Feb 2012

Test Date 15 Mar 2012

ASSEMBLY SYSTEM: OVER UNDERLAY AIRSTEP STEPSMART

The UNDERLAY used was AIRSTEP STEPSMART.

Substrate: Non-Combustible

Substrate - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring.

The Holding Torque on Specimen Frame was 2Nm.

Initial Test Specimen 1 Length Direction Critical Radiant Flux 1.7 kW/m²
Specimen 1 Width Direction Critical Radiant Flux 1.6 kW/m²
Full tests carried out in the Width Direction

SPECIMEN	Width #1	Width #2	Width #3	Mean
Critical Radiant Flux (kW/m ²)	1.6	1.4	1.6	1.5
Smoke Development Rate (%.min)	289	313	273	292

The values quoted below are as required by Specification C1.10a Fire Hazard Properties (Floors) of the Building Code of Australia. The Critical Radiant Flux quoted is the value at Flame-Out/Extinguishment (BCA General Provisions A1.1).

MEAN CRITICAL RADIANT FLUX 1.5 kW/m²

MEAN SMOKE DEVELOPMENT RATE 292 percent-minutes

OBSERVATIONS: The samples shrunk away from the heat source, ignited and burnt.



M. B. Webb
Technical Manager

DATE: 15 Mar 2012

ACCREDITED FOR
TECHNICAL
COMPETENCE

Measurement Science &
Technology No. 15393
Accredited for compliance with ISO/IEC 17025.

PAGE 1 of 2

This Page (1) has been designed to show the values required under Specification C1.10a Fire Hazard Properties (Floors) of the Building Code of Australia.

The values on Page 2 have no relevance to the Code.

1004 04 09

TIME FOR EACH SPECIMEN TO REACH EACH MARKER IN SECONDS

Specimen	50	60	110	160	210	260	310	360	410	460	510	560	610	660	710	760	810	860
1	156	157	200	224	244	292	307	331	381	480	665	1069	1470	2001	2392	/		
2	159	160	193	213	241	272	287	311	366	422	658	980	1357	1826	2283	2659	/	
3	178	179	239	267	289	323	357	395	517	675	988	1378	1751	2227	2925	/		

TESTS

SMOKE PRODUCTION

BURNING CHARACTERISTICS

Specimen	Maximum Light Attenuation (%)	Smoke Development Rate (%.min)	Burn Length (mm) at Flame Out/ Extinguishment	Time To Burn Out (s)
Initial Test: Length	73	302	714	2,931
Specimen Tests: Width				
1	76	289	740	2,692
2	81	313	780	2,896
3	63	273	740	3,512
Mean	73	292	753	3,033



ACCREDITED FOR
**TECHNICAL
COMPETENCE**

M. B. Webb
Technical Manager

DATE: 15 Mar 2012

Measurement Science
& Technology No. 15393
Accredited for compliance
with ISO/IEC 17025.

The laboratory does not allow the use of this page of the report without the use of page 1.
This page alone has no validity under specification C1.10a Fire Hazard Properties (Floors) of the Building Code of Australia.
2004 04 09 35266 18 March 2012